

ENVIRONMENTAL SEALING SILICONE GT 40

GT 40 is an elastomer developed with silicone type VMQ (ASTM D 1418). These elastomers are used for the manufacture of molded items, extruded seals, cut flash and seals vulcanized in place. They maintain their mechanical characteristics over a broad temperature range.

- Heat resistance
- Chemicals resistance
- Low degradation of properties with temperature
- Permeability and gas absorption

Properties	Standards - Test	GT 40
Elastomer		Silicone
Hardness Shore A (±5)	ASTM D 2240	40
Specific mass at 25°C (g/cm ³)	ASTM D792	1.10
Tensile strength Psi Mpa	ASTM D 412	1000 6.80
Elongation (%)	ASTM D 412	500
Residual deformation after 22 hours at 177°C (%)	ASTM D 395 Method B	30
Working temperature (°C)		-73°C to +232°C
Color		Orange

AVAILABLE FORMATS

Molded

Customized cut

Extruded

Vulcanization bonding

Sheet



